



Manufacturers and Distributors of Anti-Slip Treatments • Anti-Skid Coatings • Slip-Resistant Floor Care
• Anti-Slip FRP Panels & Step Covers • Safety Tapes • Anti-Slip Tapes

Technical Data Sheet

No Skidding® Anti-Slip Black Grit Tape #NS5200B

DESCRIPTION

No Skidding® Anti-Slip Black Grit Tape NS5200B is our 80-grit commercial / industrial grade non-skid silicon carbide grit tape that is NFSI certified for "High Traction" and meets Prop 65, ADA, and OSHA standards. It is an economical and durable solution with excellent traction and adhesion.

APPLICATIONS

No Skidding® Anti-Slip Black Grit Tape NS5200B is designed for indoor and outdoor applications that require long term adhesion to a wide variety of surfaces. It has been successfully used in a wide range of markets including OEM, MRO, Action Sports and Building Safety. Available in a wide variety of stocked and custom widths, lengths and custom die cuts.

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	TYPICAL RESULTS
Thickness	PSTC – 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.020 inch (0.508 mm) 0.002 inch (0.051 mm) 0.006 inch (0.152 mm)
Peel Adhesion To:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	90 oz/in (99 N/100 mm) 115 oz/in (126 N/100 mm)
- Powder Coated surfaces *	15 minute dwell 24 hour dwell	80 oz/in (88 N/100 mm) 85 oz/in (93 N/100 mm)
- Polyethylene	15 minute dwell 24 hour dwell	40 oz/in (44 N/100 mm) 50 oz/in (55 N/100 mm)
Shear Adhesion To:	PSTC – 107	
- Stainless Steel	½" x ½" x 1000g	5 Hours
Tack	PSTC – 6 Rolling Ball Tack	<3 inches
Coefficient of Friction (Kinetic)	ASTM D1894 - Dry Rubber - Wet Rubber - Dry Leather - Wet Leather	1.2 1.1 1.0 1.4
Service Temperature		
- High	14 days at 175°F	No visible effects, slight material shrinkage at high temperatures.
- Low	14 days at -20°F	No Visible Effect

CHEMICAL PROPERTIES	REAGENT	RECOMMENDATIONS
Solvent Resistance (Product laminated to stainless steel panel and allowed to condition for 24 hrs at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. This product is exposed to reagent for 1 hour at room temperature then reagent is removed, and product is immediately tested for scrape resistances, delaminating and other visual effects.)	Water	Recommended
	10% Salt Water	Recommended
	Bleach	Recommended
	Trichloroethylene	Not Recommended
	25% Sulfuric Acid	Recommended
	1% Sodium Hydroxide	Intermittent Contact Only
	Unleaded Gasoline	Intermittent Contact Only
	Diesel Fuel	Recommended
	Hydraulic Fluid	Recommended
	50% Antifreeze in water	Recommended
	MEK	Not Recommended
	Mineral Spirits	Recommended
99% IPA	Recommended	

- *Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.*

Note: While the data contained herein is believed to be reliable averages of the product' properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire performance data should contact No Skidding® Products for further recommendations.

WARRANTY

This product cannot eliminate the possibility of slipping. The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability of information in this document to any specific application. No Skidding® warrants its products to be free from defects but limits its obligation to replacement of products that has been proven, to No Skidding® satisfaction, to be defective. This warranty is non-transferable and only applied to customers buying directly from No Skidding® Products. No Skidding® is not liable for any loss, damage, expenses, or consequential damages arising in connection with the use of this product. E & OE. 02/18