

Manufacturers and Distributors of Anti-Slip Treatments • Anti-Skid Coatings • Slip-Resistant Floor Care • Anti-Slip FRP Panels & Step Covers • Safety Tapes • Anti-Slip Tapes

# **Technical Data Sheet**

# No Skidding<sup>®</sup> Anti-Slip White Grit Tape #NS5100W, 60 grit

## DESCRIPTION

No Skidding® NS5100W commercial grade anti-skid tape is a durable slip-resistant aluminum oxide non-slip tape that has been designed for slip-resistance and to provide a visual warning that marks possible slip and fall hazards. NS5100 series provides a high traction solution with a durable adhesive system for most commercial indoor and outdoor applications. NS5100 is NFSI certified for "High Traction" and meets Prop 65, ADA, and OSHA standards.

#### APPLICATIONS

No Skidding® Anti Slip Grit Tape NS5100 series is designed for indoor and outdoor applications that require long term adhesion to a wide variety of surfaces. It is successfully used in a wide range of markets including OEM, MRO, commercial, industrial, military. It is NFSI certified for "High Traction".

#### PROPERTIES

| PHYSICAL PROPERTIES      | TEST METHODS                                    | TYPICAL RESULTS        |
|--------------------------|---|------------------------|
| Thickness                | PSTC – 133                                      |                        |
|                          | - Substrate                                     | 0.024 inch (0.609 mm)  |
|                          | <ul> <li>Pressure Sensitive adhesive</li> </ul> | 0.002 inch (0.051 mm)  |
|                          | - Release Liner                                 | 0.006 inch (0.152 mm)  |
| Peel Adhesion To:        | PSTC – 101                                      |                        |
| - Stainless Steel        | 15-minute dwell                                 | 48 oz/in (53 N/100 mm) |
|                          | 24-hour dwell                                   | 75 oz/in (83 N/100 mm) |
| - Powder Coated surfaces | 15-minute dwell                                 | 50 oz/in (55 N/100 mm) |
|                          | 24-hour dwell                                   | 60 oz/in (66 N/100 mm) |
| - Polyethylene           | 15-minute dwell                                 | 40 oz/in (44 N/100 mm) |
|                          | 24-hour dwell                                   | 45 oz/in (49 N/100 mm) |
| Shear Adhesion To:       | PSTC – 107                                      |                        |
| - Stainless Steel        | 1⁄2" x 1⁄2" x 1000g                             | 2 hours                |
| Tack                     | PSTC – 6  |                        |
|                          | Rolling Ball Tack                               | <2 inches              |
| Coefficient of Friction  | ASTM D1894                                      |                        |
| (Kinetic)                | - Dry Rubber                                    | 1.1                    |
|                          | - Wet Rubber                                    | 1.0                    |
|                          | - Dry Leather                                   | 0.8                    |
|                          | - Wet Leather                                   | 1.3                    |
| Service Temperature      | $14 dovo at 1500 \Gamma$                        | No visible offecto     |
| - High                   | 14 days at 150ºF                                | No visible effects     |
| - Low                    | 14 days at -20⁰F                                | No Visible Effects     |

| CHEMICAL PROPERTIES                | REAGENT                 | RECOMMENDATIONS           |
|------------------------------------|-------------------------|---------------------------|
| Solvent Resistance                 | Water                   | Recommended               |
| (Product laminated to stainless    | 10% Salt Water          | Recommended               |
| steel panel and allowed to         | Bleach                  | Recommended               |
| condition for 24 hrs at room       | Trichloroethylene       | Not Recommended           |
| temperature before testing.        | 25% Sulfuric Acid       | Not Recommended           |
| Sample was covered with reagent    | 1% Sodium Hydroxide     | Intermittent Contact Only |
| to the point that edges of product | Unleaded Gasoline       | Recommended               |
| are also exposed to the reagent.   | Diesel Fuel             | Intermittent Contact Only |
| This product is exposed to reagent | Hydraulic Fluid         | Recommended               |
| for 1 hour at room temperature     | 50% Antifreeze in water | Recommended               |
| then reagent is removed and        | MEK                     | Not Recommended           |
| product is immediately tested for  | Mineral Spirits         | Recommended               |
| scrape resistances, delaminating   | 99% IPA                 | Intermittent Contact Only |
| and other visual effects.)         |                         |                           |

Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains and other treatments may vary the performance
 of the tape and should be evaluated for the compatibility of the tape to the specific surface.

**Note:** While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire performance data should contact No Skidding® Products for further recommendations.

## WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability of information in this document to any specific application. No Skidding® warrants its products to be free from defects but limits its obligation to replacement of products that has bee proven, to No Skidding® satisfaction, to be defective. This warranty is non-transferable and only applied to customers buying directly from No Skidding® Products. No Skidding® is not liable for any loss, damage, expenses, or consequential damages arising in connection with the use of this product. E & OE.