Manufacturers and Distributors of Anti-Slip Treatments • Anti-Skid Coatings • Slip-Resistant Floor Care • Anti-Slip FRP Panels & Step Covers • Safety Tapes • Anti-Slip Tapes

Technical Data Sheet

No Skidding® Anti-Slip Brown Grit Tape #NS5100BR, 60 grit

DESCRIPTION

No Skidding® NS5100BR commercial grade anti-skid tape is a durable slip-resistant aluminum oxide non-slip tape that has been designed for slip-resistance and to provide a visual warning that marks possible slip and fall hazards. NS5100 series provides a high traction solution with a durable adhesive system for most commercial indoor and outdoor applications. NS5100 is NFSI certified for "High Traction" and meets Prop 65, ADA, and OSHA standards.

APPLICATIONS

No Skidding® Anti Slip Grit Tape NS5100 series is designed for indoor and outdoor applications that require long term adhesion to a wide variety of surfaces. It is successfully used in a wide range of markets including OEM, MRO, commercial, industrial, military. It is NFSI certified for "High Traction".

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	TYPICAL RESULTS
Thickness	PSTC – 133	
	- Substrate	0.024 inch (0.609 mm)
	 Pressure Sensitive adhesive 	0.002 inch (0.051 mm)
	- Release Liner	0.006 inch (0.152 mm)
Peel Adhesion To:	PSTC – 101	
- Stainless Steel	15-minute dwell	48 oz/in (53 N/100 mm)
	24-hour dwell	75 oz/in (83 N/100 mm)
- Powder Coated surfaces	15-minute dwell	50 oz/in (55 N/100 mm)
	24-hour dwell	60 oz/in (66 N/100 mm)
- Polyethylene	15-minute dwell	40 oz/in (44 N/100 mm)
, ,	24-hour dwell	45 oz/in (49 N/100 mm)
Shear Adhesion To:	PSTC - 107	
- Stainless Steel	½" x ½" x 1000g	2 hours
Tack	PSTC - 6	
	Rolling Ball Tack	<2 inches
Coefficient of Friction	ASTM D1894	
(Kinetic)	- Dry Rubber	1.1
	- Wet Rubber	1.0
	- Dry Leather	0.8
	- Wet Leather	1.3
Service Temperature	44.4	
- High	14 days at 150°F	No visible effects
- Low	14 days at -20°F	No Visible Effects

CHEMICAL PROPERTIES	REAGENT	RECOMMENDATIONS
Solvent Resistance	Water	Recommended
(Product laminated to stainless	10% Salt Water	Recommended
steel panel and allowed to	Bleach	Recommended
condition for 24 hrs at room	Trichloroethylene	Not Recommended
temperature before testing.	25% Sulfuric Acid	Not Recommended
Sample was covered with reagent	1% Sodium Hydroxide	Intermittent Contact Only
to the point that edges of product	Unleaded Gasoline	Recommended
are also exposed to the reagent.	Diesel Fuel	Intermittent Contact Only
This product is exposed to reagent	Hydraulic Fluid	Recommended
for 1 hour at room temperature	50% Antifreeze in water	Recommended
then reagent is removed and	MEK	Not Recommended
product is immediately tested for	Mineral Spirits	Recommended
scrape resistances, delaminating	99% IPA	Intermittent Contact Only
and other visual effects.)		

Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains and other treatments may vary the performance
of the tape and should be evaluated for the compatibility of the tape to the specific surface.

Note: While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire performance data should contact No Skidding® Products for further recommendations.

WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability of information in this document to any specific application. No Skidding® warrants its products to be free from defects but limits its obligation to replacement of products that has bee proven, to No Skidding® satisfaction, to be defective. This warranty is non-transferable and only applied to customers buying directly from No Skidding® Products. No Skidding® is not liable for any loss, damage, expenses, or consequential damages arising in connection with the use of this product. E & OE.